PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : H01C 1/14, 17/28 — A1

(11) International Publication Number: WO 00/30127

(43) International Publication Date: 25 May 2000 (25.05.00)

(21) International Application Number: PCT/US99/25280

(22) International Filing Date: 28 October 1999 (28.10.99)

(30) Priority Data:
09/191,921 13 November 1998 (13.11.98) US

(71) Applicant: BOURNS, INC. [US/US]; 1200 Columbia Avenue, Riverside, CA 92705 (US).

(72) Inventors: BARRETT, Andrew, Brian; 16 The Downs, Douglas, Cork (IE). WALSH, Denis; 70 Silverdale Avenue, Ballinlough, Cork (IE).

(74) Agents: KLEIN, Howard, J. et al.; Klein & Szekeres, LLP, Suite 700, 4199 Campus Drive, Irvine, CA 92612 (US).

(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published
With international search report.

(54) Title: MULTILAYER CONDUCTIVE POLYMER DEVICE AND METHOD OF MANUFACTURING SAME

(57) Abstract

An electronic device includes two or more conductive polymer layers sandwiched between two external electrodes and one or more internal electrodes. A three-layer device is manufactured by: (1) providing a first laminated substructure comprising a first polymer layer between first and second metal layers, a second polymer layer, and a second laminated substructure comprising a third polymer layer between third and fourth metal layers; (2) forming first and second arrays of isolation apertures in the second and third metal layers, respectively; (3) laminating the first and second substructures to opposite surfaces of the second polymer layer; (4) forming first and second arrays of external electrodes in the first and fourth metal layers, respectively; (5) forming a plurality of first terminals, each connecting an external electrode in the second external electrode array to an electrode-defining area in the second metal layer, and a plurality of second terminals, each connecting an external electrode in the first external electrode array to an electrode-defining area in the third metal array; and (6) singulating the laminated structure into separate devices, each including a first polymer layer between a first external electrode and a first internal electrode, a second polymer layer between first and second internal electrodes, and a third polymer layer between the second internal electrode and a second external electrode. Each device includes a first terminal connecting the first internal electrode to the second external electrode, and a second terminal connecting the second internal electrode to the first external electrode.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	**ES**	Spain	**LS**	Lesotho	**SI**	Slovenia
AM	Armenia	**FI**	Finland	**LT**	Lithuania	**SK**	Slovakia
AT	Austria	**FR**	France	**LU**	Luxembourg	**SN**	Senegal
AU	Australia	**GA**	Gabon	**LV**	Latvia	**SZ**	Swaziland
AZ	Azerbaijan	**GB**	United Kingdom	**MC**	Monaco	**TD**	Chad
BA	Bosnia and Herzegovina	**GE**	Georgia	**MD**	Republic of Moldova	**TG**	Togo
BB	Barbados	**GH**	Ghana	**MG**	Madagascar	**TJ**	Tajikistan
BE	Belgium	**GN**	Guinea	**MK**	The former Yugoslav Republic of Macedonia	**TM**	Turkmenistan
BF	Burkina Faso	**GR**	Greece			**TR**	Turkey
BG	Bulgaria	**HU**	Hungary	**ML**	Mali	**TT**	Trinidad and Tobago
BJ	Benin	**IE**	Ireland	**MN**	Mongolia	**UA**	Ukraine
BR	Brazil	**IL**	Israel	**MR**	Mauritania	**UG**	Uganda
BY	Belarus	**IS**	Iceland	**MW**	Malawi	**US**	United States of America
CA	Canada	**IT**	Italy	**MX**	Mexico	**UZ**	Uzbekistan
CF	Central African Republic	**JP**	Japan	**NE**	Niger	**VN**	Viet Nam
CG	Congo	**KE**	Kenya	**NL**	Netherlands	**YU**	Yugoslavia
CH	Switzerland	**KG**	Kyrgyzstan	**NO**	Norway	**ZW**	Zimbabwe
CI	Côte d'Ivoire	**KP**	Democratic People's Republic of Korea	**NZ**	New Zealand		
CM	Cameroon			**PL**	Poland		
CN	China	**KR**	Republic of Korea	**PT**	Portugal		
CU	Cuba	**KZ**	Kazakstan	**RO**	Romania		
CZ	Czech Republic	**LC**	Saint Lucia	**RU**	Russian Federation		
DE	Germany	**LI**	Liechtenstein	**SD**	Sudan		
DK	Denmark	**LK**	Sri Lanka	**SE**	Sweden		
EE	Estonia	**LR**	Liberia	**SG**	Singapore		

MULTILAYER CONDUCTIVE POLYMER DEVICE AND METHOD OF MANUFACTURING SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a Continuation-in-Part of co-pending application Serial No. 09/035,196; filed March 5, 1998.

FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

Not Applicable

BACKGROUND OF THE INVENTION

The present invention relates generally to the field of conductive polymer positive temperature coefficient (PTC) devices. More specifically, it relates to conductive polymer PTC devices that are of laminar construction, with more than a single layer of conductive polymer PTC material, and that are especially configured for surface-mount installations.

Electronic devices that include an element made from a conductive polymer have become increasingly popular, being used in a variety of applications. They have achieved widespread usage, for example, in overcurrent protection and self-regulating heater applications, in which a polymeric material having a positive temperature coefficient of resistance is employed. Examples of positive temperature coefficient (PTC) polymeric materials, and of devices incorporating such materials, are disclosed in the following U.S. patents:

3,823,217 - Kampe

4,237,441 - van Konynenburg

4,238,812 - Middleman et al.

4,317,027 - Middleman et al.

4,329,726 - Middleman et al.

4,413,301 - Middleman et al.
4,426,633 - Taylor
4,445,026 - Walker
4,481,498 - McTavish et al.
4,545,926 - Fouts, Jr. et al.
4,639,818 - Cherian
4,647,894 - Ratell
4,647,896 - Ratell
4,685,025 - Carlomagno
4,774,024 - Deep et al.
4,689,475 - Kleiner et al.
4,732,701 - Nishii et al.
4,769,901 - Nagahori
4,787,135 - Nagahori
4,800,253 - Kleiner et al.
4,849,133 - Yoshida et al.
4,876,439 - Nagahori
4,884,163 - Deep et al.
4,907,340 - Fang et al.
4,951,382 - Jacobs et al.
4,951,384 - Jacobs et al.
4,955,267 - Jacobs et al.
4,980,541 - Shafe et al.
5,049,850 - Evans
5,140,297 - Jacobs et al.
5,171,774 - Ueno et al.
5,174,924 - Yamada et al.
5,178,797 - Evans

5,181,006 - Shafe et al.

5,190,697 - Ohkita et al.

5,195,013 - Jacobs et al.

5,227,946 - Jacobs et al.

5,241,741 - Sugaya

5,250,228 - Baigrie et al.

5,280,263 - Sugaya

5,358,793 - Hanada et al.

One common type of construction for conductive polymer PTC devices is that which may be described as a laminated structure. Laminated conductive polymer PTC devices typically comprise a single layer of conductive polymer material sandwiched between a pair of metallic electrodes, the latter preferably being a highly-conductive, thin metal foil. See, for example, U.S. Patents Nos. 4,426,633 - Taylor; 5,089,801 - Chan et al.; 4,937,551 - Plasko; and 4,787,135 - Nagahori; and International Publication No. WO97/06660.

A relatively recent development in this technology is the multilayer laminated device, in which two or more layers of conductive polymer material are separated by alternating metallic electrode layers (typically metal foil), with the outermost layers likewise being metal electrodes. The result is a device comprising two or more parallel-connected conductive polymer PTC devices in a single package. The advantages of this multilayer construction are reduced surface area ("footprint") taken by the device on a circuit board, and a higher current-carrying capacity, as compared with single layer devices.

In meeting a demand for higher component density on circuit boards, the trend in the industry has been toward increasing use of surface mount components as a space-saving measure. Surface mount conductive polymer PTC devices heretofore available have been generally limited to hold currents

below about 2.5 amps for packages with a board footprint that generally measures about 9.5 mm by about 6.7 mm. Recently, devices with a footprint of about 4.7 mm by about 3.4 mm, with a hold current of about 1.1 amps, have become available. Still, this footprint is considered relatively large by current surface mount technology (SMT) standards.

The major limiting factors in the design of very small SMT conductive polymer PTC devices are the limited surface area and the lower limits on the resistivity that can be achieved by loading the polymer material with a conductive filler (typically carbon black). The fabrication of useful devices with a volume resistivity of less than about 0.2 ohm-cm has not been practical. First, there are difficulties inherent in the fabrication process when dealing with such low volume resistivities. Second, devices with such a low volume resistivity do not exhibit a large PTC effect, and thus are not very useful as circuit protection devices.

The steady state heat transfer equation for a conductive polymer PTC device may be given as:

(1) $$0=[I^2R(f(T_d))]-[U(T_d-T_a)],$$

where I is the steady state current passing through the device; $R(f(T_d))$ is the resistance of the device, as a function of its temperature and its characteristic "resistance/temperature function" or "R/T curve"; U is the effective heat transfer coefficient of the device; T_d is temperature of the device; and T_a is the ambient temperature.

The "hold current" for such a device may be defined as the maximum value of I guaranteed not to trip the device from a low resistance state to a high resistance state. For a given device, where U is fixed, the only way to increase the hold current is to reduce the value of R. A hold current of 1.1A should be achievable for a single layer device, 1.8A for a two layer device and 2.6A for a three-layer polymer PTC device each having a footprint of 4.5mm

by 3.2mm.

The governing equation for the resistance of any resistive device can be stated as:

$$R=\rho L/A, \quad (2)$$

where ρ is the volume resistivity of the resistive material in ohm-cm, $\mathbb{L}$ is the current flow path length through the device in cm, and $\mathbb{A}$ is the effective cross-sectional area of the current path in cm^2. Thus, the value of $\mathbb{R}$ can be reduced either by reducing the volume resistivity ρ, or by increasing the cross-sectional area $\mathbb{A}$ of the device. The value of the volume resistivity ρ can be decreased by increasing the proportion of the conductive filler loaded into the polymer. The practical limitations of doing this, however, are noted above.

A more practical approach to reducing the resistance value $\mathbb{R}$ is to increase the cross-sectional area $\mathbb{A}$ of the device. Besides being relatively easy to implement (from both a process standpoint and from the standpoint of producing a device with useful PTC characteristics), this method has an additional benefit: In general, as the area of the device increases, the value of the heat transfer coefficient also increases, thereby further increasing the value of the hold current.

In SMT applications, however, it is necessary to minimize the effective surface area or footprint of the device. This puts a severe constraint on the effective cross-sectional area of the PTC element in device. Thus, for a device of any given footprint, there is an inherent limitation in the maximum hold current value that can be achieved. Viewed another way, decreasing the footprint can be practically achieved only by reducing the hold current value.

There has thus been a long-felt, but as yet unmet, need for very small footprint SMT conductive polymer PTC devices that achieve relatively high hold currents.

SUMMARY OF THE INVENTION

Broadly, the present invention is a conductive polymer PTC device that has a relatively high hold current while maintaining a very small circuit board footprint. This result is achieved by a multilayer construction that provides an increased effective cross-sectional area A of the current flow path for a given circuit board footprint. In effect, the multilayer construction of the invention provides, in a single, small-footprint surface mount package, two or more PTC devices electrically connected in parallel.

In one aspect, the present invention is a conductive polymer PTC device comprising, in a preferred embodiment, multiple alternating layers of metal foil and PTC conductive polymer material, with electrically conductive interconnections to form two or more conductive polymer PTC devices connected to each other in parallel, and with termination elements configured for surface mount termination.

Specifically, two of the metal layers form, respectively, first and second external electrodes. The remaining metal layers form a plurality of internal electrodes that physically separate and electrically connect two or more conductive polymer layers located between the external electrodes. The electrodes are staggered to create two sets of alternating electrodes: a first set that is in electrical contact with the first terminal, and a second set that is in electrical contact with the second terminal. One of the terminals serves as an input terminal, and the other serves as an output terminal.

A first embodiment of the invention comprises a three layer conductive polymer device having first, second, and third conductive polymer layers. In a preferred embodiment, the conductive polymer exhibits PTC characteristics. A first external electrode is in electrical contact with a first terminal and with an exterior surface of the first conductive polymer layer that is opposed to the surface facing the second conductive polymer layer. A second external

electrode is in electrical contact with a second terminal and with an exterior surface of the third conductive polymer layer that is opposed to the surface facing the second conductive polymer layer. The first and second conductive polymer layers are separated by a first internal electrode that is in electrical contact with the second terminal, while the second and third conductive polymer layers are separated by a second internal electrode that is in electrical contact with the first terminal.

In such an embodiment, if the first terminal is an input terminal and the second terminal is an output terminal, the current flow path is from the first terminal to the first external electrode and to the second internal electrode. From the first external electrode, current flows through the first conductive polymer layer to the first internal electrode and then to the second terminal. From the second internal electrode, current flows through the second conductive polymer layer to the first internal electrode and then to the second terminal, and through the third conductive polymer layer to the second external electrode and then to the second terminal.

Thus, the resulting device is a three layer device in which three layers of conductive polymer (preferably PTC) are connected in parallel. This construction provides the advantages of a significantly increased effective cross-sectional area for the current flow path, as compared with a single layer device, without increasing the footprint. Thus, for a given footprint, a larger hold current can be achieved. Alternatively, devices with only two conductive polymer layers, or with four or more such layers, can be fabricated, with similar benefits and advantages. Another aspect of the present invention is a method of fabricating the above-described devices. For a device having three conductive polymer layers, this method comprises the steps of: (1) providing (a) a first laminated substructure comprising a first conductive polymer layer sandwiched between first and second metal layers, (b) a second

conductive polymer layer, and (c) a second laminated substructure comprising a third conductive polymer layer sandwiched between third and fourth metal layers; (2) forming first and second arrays of isolation apertures in corresponding areas of the second and third metal layers; (3) laminating the first and second laminated substructures to opposite surfaces of the second conductive polymer layer to form a laminated structure comprising the first conductive polymer layer sandwiched between the first and second metal layers, the second conductive polymer layer sandwiched between the second and third metal layers, and the third conductive polymer layer sandwiched between the third and fourth metal layers, the isolation apertures being filled with polymer as a result of the lamination; (4) isolating selected areas in the first and fourth metal layers to form first and second arrays of external electrodes in the first and fourth metal layers, respectively, the external electrodes in each array being separated from each other by isolated contact areas; (5) forming a plurality of first terminals and a plurality of second terminals, each of the first terminals electrically connecting one of the electrodes in the second external electrode array to a defined area in the second metal layer through a via in a polymer-filled isolation aperture in the third metal layer, and each of the second terminals electrically connecting one of the electrodes in the first external electrode array to a defined area in the third metal layer through a via in a polymer-filled isolation aperture in the second metal layer; and (6) separating the laminated structure into a plurality of devices, each comprising two external electrodes and two internal electrodes, a first terminal electrically connecting one external electrode to one internal electrode, and a second terminal electrically connecting the other external electrode to the other internal electrode.

The step of forming the first and second terminals comprises the steps of (a) forming vias at spaced intervals in the laminated structure, each of the

vias intersecting an external electrode in each of the first and second external arrays and one of either the second or third (internal) metal layers, and passing through one of either the first or second arrays of isolation apertures; (b) plating the peripheral surfaces of the vias and adjacent surface portions of the isolated metal areas in the first and second external arrays with a conductive metal plating; and (c) overlaying a solder plating over the metal-plated surfaces.

The separation step of the fabrication process comprises the step of singulating the laminated structure into a plurality of individual conductive polymer devices, each of which has the structure described above.

In a second embodiment, a two layer device comprises a first and a second terminal, and first and second conductive polymer layers. Each conductive polymer layer has first and second opposed surfaces. The first and second conductive polymer layers are separated by a single internal electrode that is in electrical contact with the first terminal, with the second surface of the first conductive polymer layer and with the first surface of the second conductive polymer layer. The first external electrode is in electrical contact with the second terminal and with the first surface of the first conductive polymer layer. A second external electrode is in electrical contact with the second terminal and with the second surface of the second conductive polymer layer.

In a more particular embodiment of the two layer device, the second terminal is connected to the second external electrode through a via in a polymer-filled isolation aperture in the internal electrode, and the first terminal is in electrical contact with the internal electrode, while being isolated from the first and second external electrodes.

The two layer electronic device is formed by providing a first laminated substructure comprising a first conductive polymer layer sandwiched between

a first and second metal layers, and a second laminated substructure comprising a second layer of conductive polymer material laminated to a third metal layer. An array of isolation apertures is formed in the first metal layer. The first and second laminated substructures are then laminated so as to create a laminated structure, the isolation apertures becoming filled with polymer during the lamination. The laminated structure has a first conductive polymer layer sandwiched between the first and second metal layers, and a second conductive polymer layer sandwiched between the first and third metal layers. A first array of external electrodes is then formed in the third metal layer, and a second array of external electrodes is formed in the second metal layer. The external electrodes in the second and third metal layers are vertically aligned and registered with each other. The polymer-filled isolation apertures in the first metal layer are horizontally staggered between the external electrodes in the second and third metal layers. The laminated structure is then drilled to form vias (at least some of which pass through the polymer-filled isolation apertures), the vias are plated through to form a plurality of first and second terminals, and the structure is parceled into a plurality of two layer electronic devices, each having a single first terminal and a single second terminal.

During the process of formation, a plurality of first terminals is formed, each of which is in electrical contact with the first metal layer. Also, a plurality of second terminals is formed, each of which electrically connects the second and third metal layers to each other through a via in a polymer-filled isolation aperture in the first metal layer. After parceling, each electronic device produced has first and second polymer layers that operate in parallel between the first and second terminal.

In yet another embodiment, a four layer device comprises first, second, third, and fourth conductive polymer layers. The first and fourth conductive polymer layers are separated by a first internal electrode that is in electrical

contact with a first terminal. The first and second conductive polymer layers are separated by a second internal electrode that is in electrical contact with a second terminal. The second and third conductive polymer layers are separated by a third internal electrode that is in electrical contact with the first terminal.

A first external electrode is in electrical contact with the second terminal and with an exterior surface of the third conductive polymer layer that is opposed to the surface facing the second conductive polymer layer. A second external electrode is in contact with an exterior surface of the fourth conductive polymer layer that is opposed to the surface facing the first conductive polymer layer.

The device has a first terminal that electrically connects the first and third internal electrodes through a via in an isolation aperture in the second internal electrode. The device has a second terminal that electrically connects the first external electrode to the second internal electrode through a via in a polymer-filled isolation aperture in the third internal electrode, and to the second external electrode through a via in a polymer-filled isolation aperture in the first internal electrode.

The method for making a four layer device having four conductive polymer layers, is similar to that for a three layer device except that a third laminated substructure, comprising a fifth metal layer laminated to a fourth conductive polymer layer, is additionally provided in the first step. The method then proceeds as follows (from the second step):

(2) Forming first, second, and third arrays of isolation apertures in corresponding areas of the first, second, and third metal layers, respectively;

(3) Laminating the first and second laminated substructures to opposite surfaces of the second conductive polymer layer and laminating the fourth conductive polymer layer to the first metal layer to form a laminated structure

comprising the first conductive polymer layer sandwiched between the first and second metal layers, the second conductive polymer layer sandwiched between the second and third metal areas, the third conductive polymer layer sandwiched between the third layer and the fourth metal layer, and the fourth conductive polymer layer sandwiched between the first and fifth metal layers (the fourth and fifth metal layers being external metal layers); (4) Isolating selected areas of the fourth and fifth metal layers to form first and second arrays of isolated external electrodes in the fourth and fifth (external) metal layers, the electrodes in each of the first and second electrode arrays being separated from each other by an array of isolated contact areas;

(5) Forming a plurality of first terminals, each electrically connecting a defined area in the first metal layer to a defined area in the third metal layer, and forming a plurality of second terminals, each electrically connecting a defined area in the second metal layer to one of the external electrodes in the first external electrode array and to one of the external electrodes in the second external electrode array; and

(6) separating the laminated structure into a plurality of individual devices, each comprising two external electrodes and three internal electrodes, a single first terminal in electrical contact with two external electrodes and one internal electrode, and a single second terminal in electrical contact with the other two internal electrodes.

The above-mentioned advantages of the present invention, as well as others, will be more readily appreciated from the detailed description that follows.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a top plan view of a laminated structure fabricated in accordance with the present invention;

Figure 2 is an idealized cross-sectional view of the top and bottom laminated substructures and a middle conductive polymer layer, illustrating the first step in making a conductive polymer device in accordance with the method of the present invention;

Figures 3a - 3d are idealized plan views of a portion of the first, second, third and fourth metal layers of the laminated structure of Figure 1, showing their respective etch patterns;

Figure 4 is an idealized cross-sectional view, similar to that of Figure 2, after the performance of the step of creating first and second internal arrays of isolation apertures in the second and third metal layers of the laminated substructures of Figure 2;

Figure 5 is an idealized cross-sectional view showing the composite laminated structure formed after the lamination of the first and second substructures and the middle conductive polymer layer of Figure 2;

Figure 6 is a cross-sectional view of the laminated structure of Figure 5, after the performance of the step of creating first and second external arrays of isolation channel pairs respectively in the first and fourth metal layers shown in Figure 2;

Figure 7 is a top plan view of the structure of Figure 6 showing the first external array of isolation channel pairs registered in a pattern of grid lines and subsequent to the formation of vias;

Figure 8 is a cross-sectional view taken along line 8 - 8 of Figure 7, showing vias passing through isolation apertures;

Figure 9 is a top plan view of the laminated structure, after the performance of the step of depositing an insulative coating on the surface to form insulative isolation areas on the external metal areas;

Figures 10a and 10b are cross-sectional views, taken along line 10 - 10 of Figure 9, respectively prior to and subsequent to the step of metal-plating

the vias and adjacent surface portions of the external metal areas;

Figure 11 is a cross-sectional view, similar to that of Figures 10b, after the step of plating the metallized surfaces with solder;

Figure 12a is a top plan view of the laminated structure of Figure 9, after the steps of Figures 10a, 10b, 11, showing the step of singulating by cutting the laminated structure along the previously etched score lines, on the external surfaces, to form a plurality of individual conductive polymer devices;

Figure 12b is a top plan view of a singulated conductive polymer device selected from the devices shown in Figure 12a;

Figure 13 is a cross-sectional view taken along line 13 - 13 of Figure 12b;

Figure 14 is an idealized cross-sectional view of a conductive polymer layer with a metal layer on a first surface, and a laminated substructure provided as a first step in making a two-layer conductive polymer device;

Figure 15 is an idealized cross-sectional view, similar to that of Figure 14, with a first array of isolation apertures having been formed in the first metal layer;

Figure 16 is an idealized cross-sectional view of a laminated structure, after the step of laminating the components shown in Figure 15, showing a first array of isolation apertures within the laminated structure;

Figure 17 is an idealized cross-sectional view, similar to that of Figure 16, showing external arrays of isolated metal areas formed in the third and second metal layers;

Figure 18 is a cross-sectional view of a singulated two layer conductive polymer device in accordance with the present invention;

Figure 19 is an idealized cross-sectional view of the laminated substructures and an unlaminated internal conductive polymer layer provided

as a first step in making a four layer conductive polymer device in accordance with the present invention;

Figure 20 is an idealized cross-sectional view, similar to that of Figure 19, showing first, second and third internal arrays of isolation apertures formed in the first, second and third metal layers of the laminated the substructures;

Figure 21 is an idealized cross-sectional view showing the laminated structure formed by the lamination of the components shown in Figure 20;

Figure 22 is an idealized cross-sectional view, similar to that of Figure 21, showing external arrays of isolated metal areas formed in the fourth and fifth external metal layers; and

Figure 23 is a cross-sectional view of a singulated four layer conductive polymer device, in accordance with the present invention.

DETAILED DESCRIPTION OF THE INVENTION

Referring now to the drawings, Figure 1 is a plan view of a first laminated substructure 10 stacked above an unseen second laminated substructure 12 (shown in Figure 2). A conductive polymer layer of conductive polymer material (also unseen) is interposed between the first laminated substructure 10 and the second laminated substructure 12. The first laminated substructure 10, the second laminated substructure 12 and the layer, of conductive polymer material are shown in Figure 2 in an exploded sectional view taken across an arbitrary region 16 of Figure 1 bordered by dashed lines. Registration holes 18 penetrate the first laminated substructure 10, the second laminated substructure 12 and the layer of conductive polymer material and provide for positive alignment of the respective layers when alignment pins (not shown) are inserted therein.

Figure 2 shows the first laminated substructure 10, and the second

laminated substructure 12. Providing the first and second laminated substructures 10, 12 is an initial step in the process of fabricating a conductive polymer device in accordance with the present invention. The first laminated substructure 10 comprises a first conductive polymer layer 20 of conductive polymer material sandwiched between first and second metal layers 22a, 22b. A second conductive polymer layer 24 (or middle layer) of conductive polymer material is provided for lamination between the first substructure 10 and the second substructure 12 in a subsequent step in the process, as will be described below. The second substructure 12 comprises a third conductive polymer layer 26 of conductive polymer PTC material sandwiched between third and fourth metal layers 28a, 28b.

The first, second and third layers 20, 24, 26 may be made of any suitable conductive polymer composition, such as, for example, high density polyethylene (HDPE) or polyvinylidene difluoride (PVDF), into which is mixed an amount of a conductive filler (preferably carbon black) that results in the desired electrical operating characteristics. Preferably, the conductive polymer material is formulated so as to exhibit PTC characteristics in accordance with a desired set of operational criteria and specifications. Other materials, such as antioxidants and/or cross-linking agents, may also be mixed into the composition. The particular types of the constituent materials, and their proportions, depend upon the specific electrical and mechanical characteristics and specifications desired. See, for example, U.S. Patents Nos. 4,237,441 - van Konynenburg et al. and 5,174,924 - Yamada et al.

The laminated substructures 10, 12 may be fabricated by a number of methods well-known in the art. See, for example, U.S. Patents Nos. 4,426,633 - Taylor; 5,089,801 - Chan et al.; 4,937,551 - Plasko; and 4,787,135 - Nagahori. A preferred method is disclosed in U.S. Patent No. 5,802,709 - Hogge et al., assigned to the assignee of the present invention, the disclosure

of which is incorporated herein by reference.

The metal layers 22a, 22b, 28a, and 28b may be made of copper or nickel foil, with nickel being preferred for the second and third (internal) metal layers 22b, 28a. If the metal layers 22a, 22b, 28a, and 28b are made of copper foil, those foil surfaces that contact the conductive polymer layers are coated with a nickel flash coating (not shown) to prevent unwanted chemical reactions between the polymer and the copper. These polymer contacting surfaces are also preferably "nodularized", by well-known techniques, to provide a roughened surface that provides good adhesion between the metal and the polymer. Thus, the second and third (internal) metal layers 22b, 28a are both nodularized surfaces, while the first and fourth (external) metal layers 22a, 28b are nodularized only on the single surface that contacts an adjacent conductive polymer layer.

Registration holes represent one means for maintaining the substructures 10, 12 and the second layer 24 of conductive polymer in the proper relative orientation or registration for carrying out the subsequent steps in the fabrication process. Preferably, this is done by forming (e.g., by punching or drilling) a plurality of registration holes 18 in the corners of the substructures 10, 12 and the middle polymer layer 24, as shown in Figure 1. Other registration techniques, well known in the art, may also be used.

Figures 3a - 3d depict patterns that are etched through the first, second, third and fourth metal layers 22a, 22b, 28a, and 28b respectively, in the course of the following process steps. A first set of grid lines 36 and a second set grid lines 38, formed perpendicularly with the first set 36, are etched into both the first and fourth metal layers, as shown in Figures 3a and 3d. The grid lines 36, 38 form an orthogonal grid that is shown in Figures 3a-3d to illustrate how the patterns of features shown in these figures are registered with respect to each other. The grid lines 36, 38 are etched in the external (first and fourth)

metal layers 22a, 28b only, so as to form score lines that are used for singulating the laminated structure that is formed from the components shown in Figure 2 into individual conductive polymer PTC devices, as described below. The grid lines 36, 38 delineate arrays of rectangular metal areas or "parcels" on each of the respective metal layers at corresponding locations with respect to the registration holes 18, that identify the limits of individual devices to be later formed. In Figure 3c, brackets 40 show the dimensions to be assumed by an individual device (after singulation, as described below), as defined by the grid lines 36, 38 and the area contained therebetween. While the grid lines 36, 38 appear only on the first and fourth metal layers 22a, 28b (Figures 3a and 3d), they are shown in phantom outline in Figures 3b and 3c to assist in understanding the relative locations of the other structures shown in these drawings.

Figure 3a shows a first array of external isolation channels 46 formed in the first metal layer 22a. Figure 3b shows a first internal array of isolation apertures 48 formed in the second metal layer 22b. Figure 3c shows a second internal array of isolation apertures 52 formed in the third metal layer 28a. Figure 3d shows a second array of external isolation channels 46 formed in the fourth metal layer 28b.

Subsequent to scoring the resulting laminated structure along the score lines defined by the grid lines 36, 38, as described below, the first array of external isolation channels 46 forms a first external array of isolated metal areas 60 in the first metal layer 22a, separated by metal islands 61 (Figure 3a), and a second external array of isolated metal areas 62, separated by metal islands 63, in the fourth metal layer 28b (Figure 3d). The first set of score lines 36 bisects each of the first external array isolated metal areas 60 (in the first metal layer 22a) and each of the second external array of isolated metal areas 62 (in the fourth metal layer 28b).

Figures 3a, 3b 3c, and 3d depict a pattern of drill holes or vias 64 to be applied to the resulting laminated structure. The via centers are shown as addressed or registered on the centers of first and second internal arrays of isolation apertures 48, 52, respectively. The location of the via centers is common to the centers of the first and second internal arrays of isolation apertures 48, 52 in the second and third metal layers, respectively, and it is also common to the centers of the first and second arrays of metal islands 61, 63 in the first and fourth metal layers, respectively. The via locations on the first and fourth metal layers 22a, 28b are indicated by dashed circles mapped onto the metal island areas 61, 63 of Figures 3a and 3d, respectively. In the preferred embodiment, all of the vias 64 are drill holes. The diameter of the vias 64 is sufficiently smaller than the etched diameter of the isolation apertures 48, 52 so as to ensure isolation when the vias 64 are later metallized, as described below.

Figures 4 - 6 depict, in cross-sectional views similar to that of Figure 2, the successive steps of forming the etched features described above and illustrated in Figures 3a-3d. First, as shown in Figure 4, a first array of internal isolation apertures 48 (only one of which is shown in Figure 4), registered in accordance with the grid patterns of Figures 3b, is formed in the second metal layer 22b. A second array of internal isolation apertures 52, registered in accordance with the grid patterns of Figures 3c, is formed in the third metal layer 28a. As shown in Figures 3b, 3c, and 4, the first and second internal arrays of isolation apertures 48, 52 are registered in alternating parcels or metal areas defined by the grid lines 36, 38. Specifically, the internal isolation apertures 48 in the first array are positioned on an alternating grid with index locations that are between the positions of the internal isolation apertures 52 in the second array.

The removal of metal from the second and third metal layers 22b, 28a

to form the first and second arrays of internal isolation apertures 48, 52 is accomplished by conventional printed circuit board fabrication methods such as those techniques employing photoresist, masks and etching methods.

Figure 5 shows a laminated structure 42 that is the result of laminating the substructures 10, 12 and the middle conductive polymer layer 24 after ensuring that the layers are in proper registration. The middle conductive polymer layer 24 is laminated between the substructures 10, 12 by a suitable laminating method, as is well known in the art. The lamination may be performed, for example, under suitable pressure and at a temperature above the melting point of the conductive polymer material, whereby the material of the conductive polymer layers 20, 24 and 26 flows into and fills the first internal array of isolation apertures 48 and the second internal array of isolation apertures 52. The laminate 42 is then cooled to below the melting point of the polymer while maintaining pressure. At this point, the polymeric material in the laminated structure 42 may be cross-linked, by well-known methods, if desired for the particular application in which the device will be employed. The drill holes or vias 64 may then be formed in the laminate 42 at any time after the laminate 42 has cooled.

Figure 6 shows the result of masking and etching the external surfaces of the first and fourth metal layers of the laminated structure 42 with the patterns of the first and fourth metal layers of Figure 3a and 3d, respectively, to form the first and second arrays of isolation channels 46 in the first and fourth metal layers 22a, 28b, respectively. The isolation channels 46 of Figures 3a and 3d, which appear as parallel pairs of channels in Figure 6, operate, in combination with the grid lines 36, 38, to form a first external array of isolated major metal areas 60, separated by isolated contact areas or "islands" 61, in the first metal layer 22a, and a second external array of isolated major metal areas 62, separated by isolated contact areas or "islands"

63, in the fourth metal layer 28b. By way of example, one of the metal islands 61 in Figure 3a is hatched with dots to show the perimeter of an individual metal island 61. The isolated major metal areas 60 of first the external array are staggered so that each of the first external isolated metal areas 60 overlies a position between the first array of internal isolation apertures 48, and the isolated major metal areas 62 of the second external array are staggered so that each of the second external isolated metal areas 62 overlies a position between a second internal array of internal isolation apertures 52.

Each of the first internal isolation apertures 48 in the second metal layer 22b overlies a position between the second internal isolation apertures 52 in the third metal layer 28a and underlies a position between the first external isolated metal areas 60 on the first metal layer 22a. Each of the second internal isolation apertures 52 in the third metal layer 28a underlies a position between the first internal isolation apertures 48 in the second metal layer 22b and overlies a position between the second external isolated metal areas 62 on the fourth metal layer 28b.

The shape, size, and pattern of the external arrays of isolation channels 46 and the first and second internal isolation apertures 48, 52 will be dictated by the need to optimize the electrical isolation between the metal areas. The etched pattern of the first and second internal isolation apertures 48, 52 is chosen to minimize the reduction in strength of the metal layer after etching. It is important to minimize the risk of foil rupture or ripping during the lamination process. An alternating etch pattern (as shown in Figures 3b, 3c) is advantageously chosen instead of a pattern of rows to minimize the risk of rupture or tearing of inner metal foil layers during the lamination process. The amount of material etched in forming isolation apertures or in forming isolation channels for the isolated metal areas should also be kept to a minimum to obtain a maximum "active area" on the electrodes that are

formed from these areas (as described below) for a given footprint. However, it is necessary to design the isolation apertures and channels so as to provide sufficient clearances so that slight misregistrations between the layers normal in the manufacturing process does not lead to electrical shorts. In the illustrated embodiment, the external isolation channels 46 are in the form of pairs of narrow parallel bands, each pair of channels having a pair of opposed arcs 65 in the vicinity of each of the vias 64 (see Figure 7).

Figures 7 through 10a illustrate the next few steps in the fabrication process, which are performed with the laminated structure 42 oriented by means of the registration holes 18 as shown in connection with Figure 1. As shown in Figure 7, the grid lines 36, 38 have been formed, as by chemical etching, across at least one, and preferably both, of the external surfaces of the laminated structure 42. The first set of grid lines 36 comprises a parallel array of lines that are generally parallel to the external isolation channels 46, and are spaced at uniform intervals through the center lines of the vias 64, thereby bisecting each of the islands 61 and each of the isolated metal areas 60. The second set of grid lines 38 comprises a parallel array of lines that perpendicularly intersect the first set of grid lines 36 at regularly-spaced intervals, dividing the first external metal layer 22a and the fourth metal layer 28b into a grid of substantially rectangular device areas, with each device area defining the external surface limits of an individual conductive polymer device. Each device area defined in the first metal layer 22a is partitioned by a single isolation channel 46 into a first major external metal area 68a and a first minor area 70a. Each device area defined in the fourth metal layer 28b is partitioned by a single isolation channel 46 into a second major external metal area 68d and a second external minor area 70d. Thus, each external major area 68, 68d is bounded on one side by a grid line 36 separating it from an adjoining major external metal area 68, 68d, and on the opposite side by an

isolation channel 46, while each external minor area 70a, 70d is bounded on one side by an isolation channel 46 and a grid line 36 separating it from an adjoining external minor area 70a, 70d.

Referring to Figures 7 and 8, the grid lines 36, 38, in combination with the isolation channels 46 on the first and fourth external metal layers 22a, 28b, form a plurality of first and second external major areas 68a, 68d and first and second external minor areas 70a and 70d on the first and fourth metal layers 22a, 22b, respectively. Specifically, each of the islands 61, 63 is bisected by a grid line 36 into a pair of adjoining external minor metal areas 70a, 70b, respectively, while each of the external major areas 68a, 68d is likewise bisected by a grid line 36. Furthermore, each of the major metal areas 68a, 68d is separated from an adjacent external minor area 70a, 70d, by an isolation channel 46.

The grid lines 36, 38, in combination with the isolation apertures 48, 52, also define areas of the second metal layer 22b and the third metal layer 28a that form a plurality of first internal metal areas 68b in the second metal layer 22b, and a plurality of second internal metal areas 68c in the third metal layer 28a. The first external major metal areas 68a in the first metal layer 22a are in substantial vertical alignment with the second internal metal areas 68c in the third metal layer 28a, and the first internal metal areas 68b in the second metal layer 22b are in substantial vertical alignment with the second external major metal areas 68d in the fourth metal layer 28b.

The metal areas 68a, 68b 68c, 68d will serve as electrode elements in an individual device. More specifically, the first external major areas 68a will serve as first external electrodes, the first internal areas 68b will serve as first internal electrodes, the second internal electrodes, and the second external major areas 68d will serve as second external electrodes. Hereinafter, the metal areas 68a, 68b 68c, 68d will be referred to, respectively, as the first

external electrodes 68a, the first internal electrodes 68b, the second internal electrodes 68c, and the second external electrodes 68d.

As shown in Figures 7 and 8, a plurality of through-holes or "vias" 64 is punched or drilled through the laminated structure 42 at regularly-spaced intervals along each of the first set of grid lines 36, preferably approximately mid-way between each adjacent pair of the second set of grid lines 38. Because the first and second internal isolation apertures 48, 52 are staggered, as described above, the electrodes 68a, 68b 68c, 68d are also staggered relative to each other, as best shown in Figure 8. Moreover, each of the vias 64 extends through only one of the internal isolation apertures, with successive vias 64 extending alternately through a first isolation aperture 48 and a second isolation aperture 52. Specifically, referring to Figure 8, a first via 64' extends through the juncture of two adjoining first minor areas 70a, the juncture of two adjoining first internal electrodes 68b, a second internal isolation electrode 52, and the juncture of two adjoining second external electrodes 68d. A second via 64" extends through the juncture of two adjoining first external electrodes 68a, a first internal isolation aperture 48, the juncture of two adjoining second internal electrodes 68c, and the juncture of two second minor areas 70b.

Figures 9 and 10a show a thin isolating layer 74 of electrically insulating material, such as a glass-filled epoxy resin, that is formed (as by screen printing) on each of the external major surfaces of the laminated structure 42 (i.e., the top and bottom surfaces, as viewed in the drawings). The isolating layers 74 are applied so as to cover the isolation channels 46 and all but narrow peripheral edges of the first and second external electrodes 68a, 68d and narrow peripheral edges of the first and second minor metal areas 70a, 70b.

The resulting pattern of the thin isolating layers 74 leaves a series of exposed strips of metal 78 on the external surfaces of the laminated structure

42, as shown in Figure 10a, with each strip 78 presenting a regular sequence of enlarged contact regions centered on the first set of grid lines 36 on the top and bottom major surfaces of the laminated structure 42. The arcs 65 in the isolation channels 46 define a "bulge" around each of the vias 64, so that each via 64 is completely surrounded by exposed metal, as best shown in Figure 9. The isolating layers 74 are then cured by the application of heat, as is well known in the art.

The specific order of the three major fabrication steps described above in connection with Figures 6 through 9 may be varied, if desired. For example, the isolation layers 74 may be applied either before or after the vias 64 are formed, and the scoring step for forming the grid lines 36, 38 may be performed as the first, second or third of these steps.

Next, as shown in Figure 10b, all exposed metal surfaces (i.e. the series of exposed strips of metal 78) and the internal surfaces of the vias 64 are coated with a plating 80 of conductive metal, such as tin, nickel, or copper, with copper being preferred. This metal plating step can be performed by any suitable process, such as electrodeposition, for example. Then, as shown in Figure 11, the areas that were metal-plated in the previous step are again plated with a thin solder coating 82. The solder coating 82 can be applied by any suitable process that is well-known in the art, such as reflow soldering or vacuum deposition.

Finally, as shown in Figures 12a, 12b, and 13, the laminated structure 42 is singulated (by well-known techniques) along the grid lines 36, 38 to form a plurality of individual conductive polymer devices 44, one of which is shown in Figures 12b and in the sectional view of Figure 13 taken on section line 13 - 13 of Figure 12b. Because each of the first set of grid lines 36 passes through a succession of vias 64 in the laminated structure 42, as shown in Figure 7, each of the devices 44 formed after singulation has a pair of opposed

sides 84a, 84b, each of which includes a half via.

The metal plating and the solder plating of the vias 64, described above, create first and second conductive vertical columns 88a, 88b in the half vias on the opposed sides 84a, 84b, respectively. Figure 13 shows that the first conductive column 88a is in intimate physical contact with the first internal electrode 68b and the second external electrode 68d. The second conductive column 88b is in intimate physical contact with the first external electrode 68a and the second internal electrode 68c. The first conductive column 88a is also in contact with the first minor metal area 70a, while the second conductive column 88b is in contact with the second minor metal area 70b. The minor metal areas 70a, 70b (as best shown in Figure 8) are of such small area as to have a negligible current-carrying capacity, and thus do not function as electrodes, as will be seen below.

Figures 12a, 12b, and 13 also show that each device 44 includes first and second pairs of metal-plated and solder-plated conductive strips 90a, 90b along opposite edges of its top and bottom surfaces. The first and second pairs of conductive strips 90a, 90b are respectively contiguous with the first and second conductive columns 88a, 88b. The first pair of conductive strips 90a and the first conductive column 88a form a first terminal 91, and the second pair of conductive strips 90b and the second conductive column 88b form a second terminal 92. The first terminal 91 provides electrical contact with the first internal electrode 68b and the second external electrode 68d, while the second terminal 92 provides electrical contact with the first external electrode 68a and the second internal electrode 68c. The first terminal 90a is electrically isolated from the second internal electrode 68c by the polymeric material that had filled the second array of internal isolation apertures 52 during the lamination step of the process, as described above. Similarly, the second terminal 90b is electrically isolated from the first internal electrode 68b by the

polymeric material that had filled the first array of isolation apertures 48 during the lamination step.

For the purposes of this description, the first terminal 91 may be considered an input terminal and the second terminal 92 may be considered an output terminal, but these assigned roles are arbitrary, and the opposite arrangement may be employed. The current paths from the input terminal 91 to the output terminal 92 of the three layer device 44 in Figure 13 is as follows: (a) Through the first internal electrode 68b, the first conductive polymer PTC layer 20, and the first external electrode 68a; (b) through the second external electrode 68d, the third conductive polymer layer 26, and the second internal electrode 68c; and (c) through the first internal electrode 68b, the second (middle) conductive polymer layer 24, and the second internal electrode 68c. This current flow path is equivalent to connecting the three conductive polymer PTC layers 20, 24, and 26 in parallel between the input and output terminals 91, 92.

The fabrication method described above for a three layer device can adapted to make two and four layer devices, or devices with more than four layers. A two layer device provides two conductive polymer layers operating in parallel. Such a device would have a higher resistance than a comparably sized three layer device but it would also be less complex and therefore, less costly to make. A four layer device would be more complex but will provide an additional reduction in resistance for a given size than a three layer device, but at a higher cost due to the added complexity.

Figures 14-18 illustrate the steps in the method of manufacturing a two layer device. Referring first to Figure 14, a first laminated substructure 94 is shown, along with a second laminated substructure 95 on top of the first laminated substructure 94. The first and second substructures 94, 95 are provided as the initial step in the process of fabricating a two layer conductive

polymer PTC device in accordance with the present invention.

The first laminated substructure 94 comprises a first layer of conductive polymer material 96 sandwiched between first and second metal layers 98a, 98b. The second laminated substructure 95 comprises a second layer of conductive polymer material 99 with a third metal layer 98c laminated to its upper surface (as oriented in the drawings). The second metal layer 98b and the third metal layer 98c are the "external" metal layers, as shown in Figures 14 - 18.

The metal layers 98a, 98b, 98c are made of nickel foil (preferred for the internal layer 98a) or copper foil with a nickel flash coating. Those surfaces of the metal layers that are to come into contact with a conductive polymer layer are preferably nodularized, as described above in connection with the metal layers 22a, 22b, 28a, and 28b for the three layer device.

The second and subsequent steps in the method of manufacturing a two layer device are analogous to the steps illustrated in Figures 4-12, discussed above, for manufacturing a three layer device. Figure 15 shows the step of forming an array of internal isolation apertures 100 in the first metal layer 98a. The internal isolation apertures 100 (only one of which is shown in the drawings), are registered in accordance with the grid patterns previously characterized by Figures 3a-3d. That is, they are registered in alternating parcels defined by the grid lines 36, 38 (Figure 7). The metal removal from the first metal layer 98a to form the array of internal isolation apertures 100 is accomplished by conventional printed circuit board fabrication methods, such as those techniques employing photoresist, masks, and etching methods.

Figure 16 shows the next step of laminating the first substructure 94 to the second laminated substructure 95 so as to create a laminated structure 101, which is analogous to the laminated structure 42 described above in connection with Figure 5. The laminated structure 101 comprises the first

conductive polymer layer 96 sandwiched between the first metal layer 98a and second metal layer 98b, and the second conductive polymer layer 99 sandwiched between the first metal layer 98a and the third metal layer 98c.

Figure 17 shows the laminated structure after the next step of forming arrays of external isolated metal areas 102, 104 in the second and third metal layers 98b, 98c, respectively. (Only one each of the areas 102, 104 is shown in the drawings.) The isolated metal areas 102 in the second metal layer 98b and the isolated metal areas 104 in the third metal layer 98c are registered in substantial vertical alignment, i.e., one above the other. The array of internal isolation apertures 100 in the first metal layer 98a is registered between the isolated metal areas 102, 104 in the second and third metal layers 98b, 98c. The isolated metal areas 102, 104 are formed by arrays of isolation channels 107 formed in the second and third metal layers 98b, 98c. The isolation channels 107 are analogous to the isolation channels 46 described above in connection with the three layer device 44. As in the above-described three layer device 44, and analogous to the structure described above in connection with Figure 6, the pattern of the isolation channels 107 results in the isolated metal areas 102 of the second metal layer 98b being separated by isolated contact areas or "islands" 108, and the isolated metal areas 104 of the third metal layer 98c being separated by metal islands 109. The arrays of isolation apertures 100, the arrays of isolated metal areas 102, 104, the pattern of the isolation channels 107, and the arrays of metal islands 108, 109 are all patterned with respect to a pattern of grid lines, such as the grid lines 36, 38 described above in connection with Figures 3a-3d.

The laminated structure 101 is then processed in accordance with the steps described above in connection with Figures 7-12b. Figure 18 schematically shows a resulting completed two layer device 111 in section after the step of singulation described above in connection with Figures 12a

and 12b. The two layer device 111 has a first terminal 105 and a second terminal 106, each of which comprises a conductive metal plating 80 and a solder coating 82, as described above. The first metal layer 98a is formed into a middle or internal electrode 112a, the second metal layer 98b is formed into a first outer electrode 112b, and the third metal layer 98 is formed into a second outer electrode 112c.

As with the case of three layer devices, the electrodes are made of a metal foil made of a material selected from the group consisting of nickel and nickel-coated copper. An insulating layer 74 is shown on the first external electrode 112b excluding the first terminal 105 and on the surface of the second external electrode 112c excluding the second terminal 106.

The first terminal 105 is in contact with first and second minor metal areas 114a, 114b that are separated from the first and second outer electrodes 112a, 112b, respectively, by the isolation channels 107. The first terminal 105 establishes electrical contact with the internal electrode 112a, while the second terminal 106 is in electrical contact with the first and second external electrodes 112b, 112c.

Figure 18 thus shows a two layer electronic device 111 having a first (input) terminal 105 and a second (output) terminal 106, in which electrical current passes from the first terminal 105 to the second terminal 106 through the middle electrode 112a, and then through (a) the first conductive polymer layer 96 and the first external electrode 112b; and (b) the second conductive polymer layer 99 and the second external electrode 112c. Of course, the device 111 can also provide the reverse current path if the second terminal 106 is defined as the input terminal and the first terminal 105 is defined as the output terminal.

It is apparent that the fabrication method described above may be easily adapted to the manufacture of a device having any number of conductive

polymer layers greater than two. Figures 19 through 23 illustrate specifically how the fabrication method of the present invention may be modified to manufacture a device having four conductive polymer layers. For illustrative purposes only, the first few steps in the manufacture of a four layer device will be described. Figures 19 - 23 are schematic representations only intended to draw on the above discussion of the process steps illustrated in Figures 1 through 13.

Figure 19 illustrates a first laminated substructure 115a, a second laminated substructure 115b, and a third laminated substructure 115c on top of the first laminated substructure 115a. The first, second, and third substructures 115a, 115b, 115c are provided as the initial step in the process of fabricating a four layer conductive polymer device in accordance with the present invention. The first laminated substructure 115a comprises a first layer 116 of conductive polymer material sandwiched between first and second metal layers 118a, 118b. A second conductive polymer layer 120 is provided for placement between the first substructure 115a and the second substructure 115b. The second laminated substructure 115b comprises a third conductive polymer layer 122 sandwiched between third and fourth metal layers 118c, 118d. The third substructure 115c comprises a fourth layer 124 of conductive polymer material with a fifth metal layer 118e laminated to its upper surface (as oriented in the drawings). The fifth metal layer 118e and the fourth metal layer 118d are the "external" metal layers, as shown in Figures 19 - 21. The metal layers 118a-118e are made of nickel foil (preferred for the internal layers 118a, 118b, 118c) or copper foil with a nickel flash coating, and those surfaces of the metal layers that are to come into contact with a conductive polymer layer are preferably nodularized, as mentioned above.

The subsequent process steps are analogous to those discussed above with respect to Figures 3a *et seq.* Specifically, Figure 20 a shows that a first

array of internal isolation apertures 127a, registered in accordance with a pattern of grid lines (such as the grid lines 36, 38 of Figures 3b-3d), is formed in the first metal layer 118a. A second array of internal isolation apertures 127b, registered in accordance with the grid lines, is formed in the second internal metal layer 118b. The first array of internal isolation apertures 127a in the first metal layer 118a and the second array of internal isolation apertures 127b in the second metal layer 118b are registered in alternating parcels defined by the grid lines 36, 38. A third array of internal isolation apertures 127c is formed in the third metal layer 118c. The isolation apertures 118c in the third array are aligned with and in registration with the apertures 127a in the first array. The metal removal from the first, second, and third metal layers 118a, 118b, 118c to form the first, second, and third arrays of isolation apertures 127a, 127b, 127c is accomplished by conventional printed circuit board fabrication methods, such as those techniques employing photoresist, masks and etching methods.

Referring to Figure 21, while ensuring that the substructures 115a, 115b, 115c, and the second conductive polymer layer 120 are in proper registration, these substructures and the second conductive polymer layer 120 are laminated together to form a laminated structure 130. The lamination may be performed, for example, under suitable pressure and at a temperature above the melting point of the conductive polymer material, whereby the material of the conductive polymer layers 116, 120, 122, and 124 flows into and fills the isolation apertures 127a, 127b, and 127c. The laminate is then cooled to below the melting point of the polymer while maintaining pressure. At this point, the polymeric material in the laminated structure 130 may be cross-linked, by well-known methods, if desired for the particular application in which the device will be employed.

Referring now to Figure 22, after the laminated structure 130 of Figure

21 has been formed, arrays of external isolation channels 46 are etched into the fourth metal layer 118d (the first or bottom external metal layer) and the fifth metal layer 118e (the second or top external metal layer). As explained above, in connection with Figures 3a and 3d and Figure 6 - 8, the isolation channels 46 appear as parallel pairs of channels or brackets. The formation of the external isolation channels 46 in the fourth and fifth metal layers 118d, 118e creates, in combination with parceling along the grid lines 36, 38 (shown in Figures 3a, 3d, and 7), a first external array of isolated major metal areas 60 on the fifth metal layer 118e and a second external array of isolated major metal areas 62 on the fourth metal layer 118d. The isolation channels 46 also create a first array of metal islands 61 between each adjacent pair of major metal areas 60 in the fifth metal layer 118e, and a second array of metal islands between each adjacent pair of major metal areas 62 in the fourth metal layer 118d.

The isolated major metal areas 60 in the fifth metal layer 118e are staggered so that each of them overlies a position between a pair of the internal isolation apertures 127a. The isolated major metal areas 62 in the fourth metal layer 118d are staggered so that each of them underlies a position between a pair of internal isolation apertures 127c in the third array. Each internal isolation aperture 127a in the first metal layer 118a overlies a position between internal isolation apertures 127b in the second metal layer 118b. Each internal isolation aperture 127b in the second metal layer 118b underlies a position between first internal isolation apertures 127a in the first metal layer 118a and overlies a position between internal isolation apertures 127c in the third metal layer 118c. Each of the internal isolation apertures 127a in the first array also underlies a position directly below a first external isolated major metal area 60 in the fifth metal layer 118e and overlies a position directly above a second external isolated major metal area 62 in the fourth metal layer 118d. As will

be seen, the arrays of external major metal areas 60, 62 provide pluralities of first and second external electrodes, and the first, second, and third (internal) metal layers provide a plurality of first, second, and third internal electrodes, respectively.

Referring now to Figure 23, the fabrication process proceeds as describe above with reference to Figures 8-13. After singulation, the result is a device 150 that is similar to that shown in Figures 12b and 13, except that there are four conductive polymer layers separated by three internal electrodes. The resulting device 150 is electrically equivalent to four conductive polymer elements connected in parallel between an input terminal an output terminal.

Specifically, the device 150 comprises first, second, third, and fourth conductive polymer layers 116, 120, 122, 124 respectively. The first and fourth conductive polymer layers 116, 124 are separated by a first internal electrode 132a that is in electrical contact with a first terminal 156a. The first and second conductive polymer layers 116, 120 are separated by a second internal electrode 132b that is in electrical contact with a second terminal 156b. The second and third conductive polymer layers 120, 122 are separated by a third internal electrode 132c that is in electrical contact with the first terminal 156a. A first external electrode 132d is in electrical contact with the second terminal 156b and with a surface of the third conductive polymer layer 122 that is opposed to the surface facing the second conductive polymer layer 120. A second external electrode 132e is in electrical contact with the second terminal 156b and with a surface of the fourth conductive polymer layer 124. The opposite surface of the conductive polymer layer 124 faces the first conductive polymer layer 116. Insulative isolation layers 138, similar to the insulation layers 74, described above with reference to Figure 9 and Figure 10, cover the portions of the external electrodes 132d, 132e between the terminals 156a, 156b. The terminals 156a, 156b are formed by the metal plating and

solder plating steps described above with reference to Figures 10b and 11.

If the first terminal 156a is arbitrarily chosen as an input terminal, and the second terminal 156b is arbitrarily chosen as the output terminal, the current path through the device 150 is as follows: From the input terminal 156a, current enters the first and third internal electrodes 132a, 132c. From the first internal electrode 132a, current flows (a) through the fourth conductive polymer layer 124 and the second external electrode 132e to the output terminal 156b; and (b) through the first conductive polymer PTC layer 116 and the second internal electrode 132b to the output terminal 156b. From the third internal electrode 132c, current flows (a) through the second conductive polymer layer 120 and the second internal electrode 132b to the output terminal 156b; and (b) through the third conductive polymer layer 122 and the first external electrode 132d to the output terminal 156b.

It will be appreciated that the device constructed in accordance with the above described fabrication process is very compact, with a small footprint, and yet it can achieve relatively high hold currents.

While exemplary embodiments have been described in detail in this specification and in the drawings, it will be appreciated that a number of modifications and variations may suggest themselves to those skilled in the pertinent arts. For example, the fabrication process described herein may be employed with conductive polymer compositions of a wide variety of electrical characteristics, and is thus not limited to those exhibiting PTC behavior. Furthermore, while the present invention is most advantageous in the fabrication of SMT devices, it may be readily adapted to the fabrication of multilayer conductive polymer devices having a wide variety of physical configurations and board mounting arrangements. These and other variations and modifications are considered the equivalents of the corresponding structures or process steps explicitly described herein, and thus are within the

scope of the invention as defined in the claims that follow.

WHAT IS CLAIMED IS:

1. A method of fabricating an electronic device, comprising the steps of:

(1) providing (a) a first laminated substructure comprising a first conductive polymer layer sandwiched between first and second metal layers, (b) a second conductive polymer layer, and (c) a second laminated substructure comprising a third conductive polymer layer sandwiched between third and fourth metal layers;

(2) forming first and second arrays of internal isolation apertures in corresponding areas in the second and third metal layers;

(3) laminating the first and second laminated substructures to opposite surfaces of the second conductive polymer layer to form a laminated structure;

(4) forming an array of first external electrodes in the first metal layer and an array of second external electrodes in the fourth metal layer;

(5) forming a plurality of first terminals and a plurality of second terminals, each of the first terminals electrically connecting one of the second external electrodes to a defined area of the second metal layer through an isolation aperture in the third metal layer, and each of the second terminals electrically connecting one of the first external electrodes to a defined area of the third metal layer through an isolation aperture in the second metal layer; and

(6) separating the laminated structure into a plurality of devices, each comprising a first terminal and a second terminal.

2. The method of Claim 1, wherein the metal layers are made of a metal foil.

3. The method of Claim 1, wherein the step of forming the first and

second internal arrays of isolation apertures in the second and third metal layers comprises the step of removing selected portions of the second and third metal layers; and

wherein the step of forming the arrays of first and second external electrodes comprises the step of removing selected portions of the first and fourth metal layers.

4. The method of Claim 3, wherein the steps of removing selected portions of the first, second, third, and fourth metal layers are performed so that each of the first external electrodes is in substantial vertical alignment with a defined area of the third metal layer, and so that each of the second external electrodes is in substantial vertical alignment with a defined area of the second metal layer.

5. The method of Claim 4, wherein the step of forming the pluralities of first and second terminals comprises the steps of:

(5)(a) forming a first plurality of vias through the laminated structure, each passing through one of the internal isolation apertures in the first array, and forming a second plurality of vias through the laminated structure, each passing through one of the internal isolation apertures in the second array; and

(5)(b) metallizing the interior surface of each of the vias in the first and second plurality of vias.

6. The method of Claim 5, wherein the step of metallizing comprises the steps of:

(5)(b)(i) plating the interior via surfaces with a metal selected from the group consisting of tin, nickel, and copper; and

(5)(b)(ii) coating the plated interior via surfaces with solder.

7. The method of Claim 5, further comprising, after the step of forming the vias and before the step of metallizing, the step of forming an isolation layer of insulative material on each of the first and fourth metal layers, the isolation layers being formed so as to leave exposed a portion of each metal layer adjacent each of the vias.

8. The method of Claim 7, wherein the isolation layers are formed of glass-filled epoxy resin.

9. The method of Claim 7, wherein the step of metallizing is performed so as to metallize the exposed portions of each metal layer adjacent each of the vias.

10. An electronic device, comprising:

a first terminal and a second terminal;

a first electrode in electrical contact with the first terminal;

and

first and second conductive polymer layers, each having a first surface in electrical contact with the first electrode and a second surface electrically connected to the second terminal.

11. The electronic device of Claim 10, further comprising:

a second electrode in physical contact with the second surface of the first conductive polymer layer and electrically connected to the second terminal; and

a third electrode in physical contact with the second surface of the second conductive polymer layer and electrically connected to the second terminal.

12. The electronic device of Claim 11, wherein the second electrode has first and second opposed surfaces, the first surface of the second electrode being in physical contact with the second surface of the first conductive polymer layer, the device further comprising:

a third conductive polymer layer having a first surface in physical contact with the second surface of the second electrode and a second surface in electrical contact with the first terminal.

13. The electronic device of Claim 12, further comprising:

a fourth electrode in physical contact with the second surface of the third conductive polymer layer and in electrical contact with the first terminal.

14. The electronic device of Claim 11, wherein the first electrode is electrically isolated from the second terminal by conductive polymer, and wherein the second and third electrodes are electrically isolated from the first terminal by conductive polymer.

15. The electronic device of Claim 11, wherein the first, second, and third electrodes are made of a metal foil.

16. An electronic device, comprising:

first and second terminals;

first, second, and third conductive polymer layers, each having first and second opposed surfaces;

the first and second conductive polymer layers being separated by a first internal electrode that is in electrical contact with the first terminal, the second surface of the first conductive polymer layer and the first surface of the

second conductive polymer layer;

the second and third conductive polymer layers being separated by a second internal electrode that is in electrical contact with the second terminal, the second surface of the second conductive polymer layer, and the first surface of the third conductive polymer layer;

a first external electrode in electrical contact with the second terminal and with the first surface of the first conductive polymer layer; and

a second external electrode in electrical contact with the first terminal and with the second surface of the third conductive polymer layer.

17. The electronic device of Claim 16, further comprising:

a first insulating layer on the first external electrode excluding the first terminal; and

a second insulating layer on the second external electrode excluding the second terminal.

18. The electronic device of Claim 17, wherein the insulating layer is made of glass-filled epoxy resin.

19. The electronic device of Claim 16, wherein each of the first and second terminals comprises:

a first layer formed of a metal selected from the group consisting of tin, nickel, and copper; and

a second layer formed of solder.

20. The electronic device of Claim 16, wherein the first and second external electrodes and the first and second internal electrodes are made of a metal foil.

21. An electronic device, comprising:

first and second terminals;

first and second conductive polymer layers, each having first and second opposed surfaces;

the first and second conductive polymer layers being separated by an internal electrode that is in electrical contact with the first terminal, the second surface of the first conductive polymer layer, and the first surface of the second conductive polymer layer;

a first external electrode being in electrical contact with the second terminal and with the first surface of the first conductive polymer layer; and

a second external electrode being in electrical contact with the second terminal and with the second surface of the second conductive polymer layer.

22. The electronic device of Claim 21, wherein the internal electrode and the first and second external electrodes are made of a metal foil.

23. The electronic device of Claim 21, further comprising:

a first insulating layer on the first external electrode excluding the first terminal; and

a second insulating layer on the second external electrode excluding the second terminal.

24. A laminated structure for parceling into a plurality of electronic devices, each electronic device having a first terminal and a second terminal, the structure comprising:

a first conductive polymer layer sandwiched between first and second metal layers, and a second conductive polymer layer sandwiched between the first metal layer and a third metal layer;

an array of polymer-filled isolation apertures formed in the first metal layer;

a first array of isolated metal areas in the third metal layer; and

a second array of isolated metal areas in the second metal layer, the isolated metal areas in the second and third metal layers being registered with each other in substantial vertical alignment, the array of polymer-filled isolation apertures in the first metal layer being registered between the isolated metal areas in the second and third metal layers;

a plurality of first terminals, each of which is in electrical contact with the first metal layer, while being electrically isolated from the isolated metal areas in the second and third metal layers; and

a plurality of second terminals, each of which electrically connects an isolated metal area in the second metal layer to an isolated metal area in the third metal layer through a polymer-filled isolation aperture in the first metal layer.

25. A method of fabricating an electronic device, comprising the steps of:

(1) providing (a) a first laminated substructure comprising a first conductive polymer layer sandwiched between first and second metal layers, and (b) a second laminated substructure comprising a second conductive polymer layer laminated to a third metal layer;

(2) forming an array of internal isolation apertures in the first metal layer;

(3) laminating the first and second laminated substructures together so as to create a laminated structure comprising the first conductive polymer layer sandwiched between the first and second metal layers, and the second conductive polymer layer sandwiched between the third and first metal layers,

with the isolation apertures being filled with conductive polymer material as a result of the laminating step;

(4) forming a first array of external electrodes in the third metal layer, and a second array of external electrodes in the second metal layer, the external electrodes in the first and second external electrode arrays being registered in substantial vertical alignment with each other, the polymer-filled isolation apertures in the first metal layer being registered between the external electrodes in the first and second external electrode arrays;

(5) forming a plurality of first terminals, each of which is in electrical contact with a defined area in the first metal layer, while being electrically isolated from the external electrodes in the first and second external electrode arrays; and

(6) forming a plurality of second terminals, each of which electrically connects an external electrode in the first external electrode array to an external electrode in the second external electrode array through a polymer-filled isolation aperture in the first metal layer.

26. The method of Claim 25, further comprising the step of:

(7) separating the laminated structure into a plurality of electronic devices, each of which includes a first terminal and a second terminal.

27. A method of fabricating an electronic device, comprising the steps of:

(1) providing (a) a first laminated substructure comprising a first conductive polymer layer sandwiched between first and second metal layers, (b) a second conductive polymer layer, and (c) a second laminated substructure comprising a third conductive polymer layer sandwiched between third and fourth metal layers, and (d) a third laminated substructure comprising

a fourth layer of conductive polymer material laminated to a fifth metal layer;

(2) forming first, second, and third arrays of internal isolation apertures in the first, second, and third metal layers, respectively;

(3) laminating the first and second laminated substructures to opposite surfaces of the second conductive polymer layer and laminating the third substructure to the first laminated substructure so as to create a laminated structure comprising the first conductive polymer layer sandwiched between the first and second metal layers, the second conductive polymer layer sandwiched between the second and third metal layers, the third conductive polymer layer sandwiched between the third and fourth metal layers, and the fourth conductive polymer layer sandwiched between the first and fifth metal layers;

(4) forming a first array of external electrodes in the fifth metal layer and a second array of external electrodes in the fourth metal layer, whereby the external electrodes in the first and second external electrode arrays are registered in substantial vertical alignment with the isolation apertures in the second internal electrode array, and whereby the isolation apertures in the first and third aperture arrays are in substantial vertical alignment with each other;

(5) forming a plurality of first terminals, each first terminal electrically connecting a defined area in the first metal layer with a defined area in the third metal layer through a polymer-filled isolation aperture in the second aperture array; and

(6) forming a plurality of second terminals, each second terminal electrically connecting an external electrode in the second external electrode array to a defined are in the second metal layer through a polymer-filled isolation aperture in the first aperture array, and to an external electrode in the first external electrode array through a polymer-filled isolation aperture in the third aperture array.

28. The method of Claim 27, wherein the metal layers are made of a metal foil.

29. The method of Claim 27, wherein the separating step comprises the step of:

(7) separating the laminated structure into a plurality of devices, each having a first conductive polymer layer sandwiched between a first external electrode and a first internal electrode, a second conductive polymer layer sandwiched between a first internal electrode and a second internal electrode, a third conductive polymer layer sandwiched between a second internal electrode and a third internal electrode and a fourth conductive polymer layer sandwiched between a third internal electrode and a second external electrode, with each of the first terminals being in electrical contact only with the first and third internal electrodes and each of the second terminals only being in electrical contact with the first and second external electrodes and the second internal electrode.

30. The method of Claim 27, wherein the steps of forming the pluralities of first and second terminals comprises the steps of:

forming first and second pluralities of vias through the laminated structure, each of the first plurality of vias passing through an isolation aperture in each of the first and third metal layers, and each of the second plurality of vias passing through the an isolation aperture in the second layer; and

metallizing the interior surface of each of the vias.

31. The method of Claim 30, wherein the step of metallizing comprises

the steps of:

plating the interior via surfaces with a metal selected from the group consisting of tin, nickel, and copper; and

coating the plated interior via surfaces with solder.

32. The method of Claim 30, further comprising, after the step of forming the vias and before the step of metallizing, the step of forming an isolation layer of insulative material on each of the external electrodes, each of the isolation layers being configured so as to cover one of the external electrodes and to leave exposed a portion of each metal area adjacent each of the vias.

33. The method of Claim 32, wherein the isolation layers are formed of glass-filled epoxy resin.

34. The method of Claim 32, wherein the step of metallizing is performed so as to metallize the exposed portions of each metal area adjacent each of the vias.

FIG. 1



FIG. 2



FIG. 3a





FIG. 3b



FIG. 3c



FIG. 3d



FIG. 4


42
22a
20
48
22b
24
52
52
28a
26
28b

FIG. 5


42
46
61
46
60
46
61
46
28a
20
48
22b
24
52
52
28a
26
28b
62
46
63
46
62

FIG. 6


38
46
64
65
68a
36
70a
40
8
63

FIG. 7


42
46
70a
68a
64'
64"
64
48
68b
68c
68d
52
20
24
26
70b

FIG. 8


78
78
78
65
64
65
64
74
46
46
76
76
10
10
65
65
65
64
64
64

FIG. 9


42
70a
46
74
78
46
70a
68a
68a
64
64
46
20
20
68b
68b
48
24
24
52
68c
68c
26
26
68d
68d
74
70b
70b

FIG. 10a



FIG. 10b



FIG. 11



FIG. 12a



FIG. 12b


44
92
91
90b
74
70a
90a
68a
20
68b
24
68c
26
88b
88a
68d
70a
74

FIG. 13


95
98c
99
94
98a
96
98b

FIG. 14



FIG. 15



FIG. 16



FIG. 17


114a
105
107
74
106
111
112b
82
80
99
80
82
112a
100
96
112c
107
74
114b

FIG. 18


115c
118e
124
118a
115a
116
118b
120
118c
115b
122
118d

FIG 19


118e
115c
124
118a
127a
115a
116
127b
118b
127b
120
118c
127c
115a
122
118d

FIG. 20


118e
130
124
127a
118a
127b
118b
127b
116
118b
120
127c
118c
118c
122
118d

FIG. 21


130
46
61
46
60
118e
46
61
46
124
127a
118a
127b
116
127b
118b
120
127c
118c
122
46
63
46
118d
62
46
63
46

FIG. 22


46
138
132e
156b
130
124
132a
116
156a
132b
120
132c
122
132d
46
138

FIG. 23

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/25280

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01C1/14 H01C17/28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 H01C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 29879 A (IKEDA TAKASHI ;KOJIMA JUNJI (JP); MATSUSHITA ELECTRIC IND CO LTD () 9 July 1998 (1998-07-09) English abstract and figures	10-17, 20-24
A		1-9,18, 19,25-34

X	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 07, 31 July 1997 (1997-07-31) & JP 09 069416 A (TDK CORP), 11 March 1997 (1997-03-11) abstract	10-17, 20-24
A		1-9,18, 19,25-34

	-/--	

[X] Further documents are listed in the continuation of box C.

[X] Patent family members are listed in annex.

° Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
14 January 2000	26/01/2000

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL – 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Odgers, M

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Inter: nal Application No
PCT/US 99/25280

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document. with indication,where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 089 801 A (CHAN CHI-MING ET AL) 18 February 1992 (1992-02-18) cited in the application column 7, line 10-60	1,10,16, 21,24, 25,27
A	US 4 769 901 A (NAGAHORI ATSUSHI) 13 September 1988 (1988-09-13) cited in the application column 3, line 4-26 column 4, line 30-35	1,5,6, 10,16, 21,24, 25,27, 30,31
A	EP 0 853 323 A (RAYCHEM CORP) 15 July 1998 (1998-07-15) claims 1-4,8,10; figures 5,6	1,5,6, 10,16, 21,24, 25,27, 30,31

1

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 99/25280

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9829879 A	09-07-1998	EP 0955643 A	10-11-1999
JP 09069416 A	11-03-1997	NONE	
US 5089801 A	18-02-1992	AT 147882 T	15-02-1997
		CA 2092807 A	29-03-1992
		DE 69124256 D	27-02-1997
		DE 69124256 T	14-08-1997
		EP 0551384 A	21-07-1993
		HK 1006888 A	19-03-1999
		JP 6501817 T	24-02-1994
		US 5436609 A	25-07-1995
		WO 9206477 A	16-04-1992
US 4769901 A	13-09-1988	JP 1972106 C	27-09-1995
		JP 6090962 B	14-11-1994
		JP 62230001 A	08-10-1987
		DE 3707493 A	01-10-1987
		US 4876439 A	24-10-1989
EP 0853323 A	15-07-1998	CA 2190361 A	23-11-1995
		CN 1148441 A	23-04-1997
		DE 69504333 D	01-10-1998
		DE 69504333 T	12-05-1999
		EP 0760157 A	05-03-1997
		JP 10500255 T	06-01-1998
		WO 9531816 A	23-11-1995
		US 5831510 A	03-11-1998